



Gold-in-a-Box™ Conjugation Kit

For preparing highly reactive antibody (purified) and protein (purified and soluble) gold conjugates

Cat. #: NGIB34-B018

Introduction

Lateral flow chromatographic and flow-through tests offer fast detection of critical components for use in point-of-care testing. The key to these tests is the ability to covalently attach antibodies to intensely colored, nanometer particles. Gold sols that bind ligands through a sulfur bond have proven highly successful for this application. For optimal binding of the antibody or protein while retaining a high degree of specific activity, the pH of the gold sol must be adjusted to slightly above the isoelectric point of the coating antibody or protein. This is done through a series of pH titrations with the provided buffers. Varying amounts of Buffers A and B, and varying amounts of Buffers C and D are added to the gold to create a pH 5-11 range. Next, antibody or protein is added and after 30 minutes the reaction is stopped. This convenient Gold-in-a-Box™ kit allows you to quickly (in less than 50 minutes) determine the pI and optimal coating range for your antibody or soluble protein.

Kit Components

1. NG30-B009 - Naked Gold® Sol – 30 nm - 15 OD - 9 mL
2. NG40-B009 - Naked Gold® Sol – 40 nm - 15 OD - 9 mL
3. BUFA-001 - Buffer Solution A – 1.0 mL (cap with black dot)
4. BUFB-001 - Buffer Solution B – 1.0 mL (cap with green dot)
5. BUFC-001 - Buffer Solution C – 1.0 mL (cap with blue dot)
6. BUFD-001 - Buffer Solution D – 1.0 mL (cap with red dot)
7. BLK-002 - BSA Blocking Solution – 2.0 mL (clear cap)
8. CDB-002 - Conjugate Drying Buffer – 2.0 mL (cap with purple dot)

Materials required but not provided

1. Clean glass or polystyrene test tubes (12 × 75 mm)
2. Pipettes and tips

Sample Preparation

The antibodies or proteins used with this kit must be at a concentration of 1 mg/mL or greater and should be in a 0.5 X PBS buffer solution. If they are not in a 0.5 X PBS buffer solution, then dialyze the antibody or protein against 0.5 X PBS. Proteins at a concentration of 2 mg/mL or greater should be in 1 X PBS.

Generic Procedure

Note: Use aseptic technique when handling the gold sol

1. Shake or swirl gold to re-suspend any settled gold. Place 0.5 mL Naked Gold sol into ten (10) clean individual test tubes.
2. Label each tube with the pH value (or, 1 through 10) from the provided pH charts.
3. Use the pH charts to add varying amounts of buffer in microliters to each test tube. Shake to mix.
4. Place each tube on a low speed vortexer and add antibody solution (See Sample Preparation Section) - mix thoroughly (about 2 to 3 seconds).

Ideally, for the 40 nm gold, 7 µL of a 2 mg/mL solution of antibody or protein is optimal. For the 30 nm gold, ideally, 10.5 µL of a 2 mg/mL solution of antibody or protein is optimal.

Note: The saturation point for 40 nm gold is typically near 30 mcg of antibody per mL of gold. The saturation point for 30 nm gold is about 45 µg of antibody per mL of gold.

5. A deepening purple color, a black precipitate or both on some tubes indicates that the antibody or protein is below its isoelectric point, leading to cross-linking of individual gold sols. Cross-linked sols cannot be used in immunological assays and should be discarded. Deep purple sols are usually mostly inactive as well. Only tubes with a slight purple color or no change in color are useful for immunological assays.
6. Allow the reaction to continue for a total of 30 minutes.

Note: See section below on “Stability of Gold Conjugates”.

7. Stop the reaction by the addition of 50 µL of Blocking Stabilizer Solution.

Note: In some conjugates that result in non-specific reactivity, it is often best to allow the blocker to react for an additional 16 hours at room-temperature.

Please Note: This generic procedure may be modified or scaled as needed. When developing a new assay, it is important to determine the optimal amount of ligand to add to the gold particles. Once the tubes have been assayed, it is useful to further optimize binding by both decreasing or increasing the amount of antibody added to each tube. Often, a 20% increase or decrease in antibody or protein added is sufficient to yield an optimal coating procedure. A few cases require a 40% or more increase or decrease in coating antibody or protein.

Stability of Gold Conjugates

Gold particles completely coated with protein take on the properties of the coating proteins and become very stable in solutions of high ionic strength. An excellent way to test the effectiveness of the conjugation reaction is to combine 10 µL of coated gold sol (prior to the addition of the BSA blocking solution) with 10 µL of 1 M NaCl. Sols with incomplete coating will fall out of solution (turn black), while completely coated sols will remain stable (red).

Testing of BSA Blocked Gold Conjugate

The conjugate is now ready for use in a rapid assay at nominal usage of 5-15 µL per assay. Tubes that have a slight color change and ones with no color change should be assayed for optimal activity. Tubes with the best activity are usually a good indicator of the approximate isoelectric point of the coated antibody or protein.

Gold Conjugate Drying Procedure

In order to effectively dry down the gold, add 0.1 mL of Gold Drying Buffer for every 1.0 mL of conjugate. Mix thoroughly. Apply gradually and evenly to either glass fiber or polyester ribbon.

Place **polyester ribbon** in a vented 37° C oven or incubator for four (4) hours to dry thoroughly. **Glass fiber** ribbon should be left in the incubator overnight.

The following alternative drying procedure is for polyester ribbon only

If a vented incubator is not available, use a hairdryer set to deliver 30-37°C heat at a ten inch (25 cm) distance from the ribbon surface. Usually, three (3) or four (4) minutes in a wave-motion will suffice to thoroughly dry the ribbon.

Store all dried ribbons in a glass tightly sealable container containing ample desiccants (granular or pouch-form).

Discussion

A sensitive lateral flow assay requires that all of the antibody or protein that is added to the gold sol be irreversibly bound to the beads. Any free antibody or protein serves to short-circuit the assay. This behavior ultimately sets the sensitivity limits of an assay.

Nano-gold particles remain in solution because they repel each other due to a significant negative charge. This means that proteins bind to gold particles through both ion-exchange attraction and covalent bonding of protein thiols (-SH) with surface gold. The challenge for preparing stable gold conjugates in this Gold-in-a-Box format depends upon one's ability to manage the binding of antibody or proteins at or near their isoelectric point. In a few cases, the titration of the pH may need to be fine-tuned.

The antibodies or proteins in the sample must display a suitable number of surface thiols (-SH). Proteins with no surface thiol groups bind exchangeably with gold particles through ion-exchange interactions. Such proteins do not form stable gold sols that are suitable for flowing chromatographic assays. Equally problematic are protein preparations where surface thiols have been capped or protected by reaction with N-ethyl maleimide or iodoacetic acid.

Application of Gold conjugates

Stabilized gold conjugates made from concentrated sols are ready for use in lateral flow and flow-through assays without additional optimizations. Typically, 5-15 µL gold conjugate per test will give optimally sensitive assays.

The gold conjugate is excellent for use in a variety of gold amplified assay procedures. This includes BioAssay Works' patented ultra-sensitive C-FLAT technology. Researchers interested in evaluating this technology may contact BioAssay Works for a research use license with no fee.

pH Charts for Optimal coating at a pH of 5-11 (per 0.5 mL of gold)

Tube Number	pH	Buffer A	Buffer B
1	5.4	9 µL	1 µL
2	6.6	8 µL	2 µL
3	7.3	6 µL	4 µL
4	7.8	4 µL	6 µL
5	8.2	2 µL	8 µL

Tube Number	pH	Buffer C	Buffer D
6	8.4	10 µL	0 µL
7	8.8	8 µL	2 µL
8	9.2	6 µL	4 µL
9	9.6	4 µL	6 µL
10	10.1	2 µL	8 µL

Please Note:

All buffers and the BSA blocking solution contain less than 0.1 % of Proclin® 950.

ProClin is corrosive. Direct contact with components that contain ProClin should be avoided. ProClin is harmful if inhaled, ingested or absorbed by the skin. Avoid contact with skin, eyes, or clothing. Wear eye or face protection when handling. If skin or eye contact occurs, wash with copious amounts of water. If ingested or inhaled, contact a physician immediately.

Handling: Do not eat, drink, smoke or apply cosmetics in laboratory areas. Do not mouth-pipette reagents or samples. Avoid splashing and forming aerosols. Use reagents according to the product insert.

Storage: The BSA Blocking Solution must be stored refrigerated, 2-8°C. All other kit components may be stored at room temperature, 20-25°C.

- The entire kit may be stored refrigerated, 2-8°C.
- **Do NOT Freeze**
- Make sure all components reach room temperature before use.

Warranty

These products are warranted to perform as described in their labeling and in BioAssay Works®, LLC literature when used in accordance with their instructions. THERE ARE NO WARRANTIES, WHICH EXTEND BEYOND THIS EXPRESSED WARRANTY, AND BIOASSAY WORKS, LLC DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR PARTICULAR PURPOSE. BioAssay Works', LLC sole obligation and purchaser's exclusive remedy for breach of this warranty shall be, at the option of BioAssay Works, LLC, to repair or replace the products. In no event shall BioAssay Works, LLC be liable for any proximate, incidental, or consequential damages in connection with the products.

This product is for internal research use only and may not be resold or used for provision of any services to a third party for paid consideration.